

NitCal™

Item No 0567/E

Corrosion inhibitor for extending corrosion lifetime through increased concrete resistance

NitCal™ is a registered trade mark of Yara International ASA

FIELDS OF APPLICATION

NitCal[™] is a corrosion inhibiting admixture designed to avoid corrosion of reinforced and prestressed concrete.

Corrosion is the major structural threat to concrete constructions.

NitCal™ improves the durability of reinforced concrete at the level of the concrete and the rebar:

- NitCal[™] -based admixtures provide corrosion inhibition for reinforcements. Forming protective hydroxide layers around the reinforcements and enhancing chloride fixation promotes rebar durability
- NitCalTM -based admixtures increase strength and reduces porosity of the concrete itself, which leads to an improved resistance towards water and chlorides migration as well as against mechanical stress.

DOSAGE

The general dosage range is 2.0-4.0 mass-% of the cement content.

STANDARD COMPLIANCE

NitCal[™] is a corrosion inhibiting admixture matching all requirements according to ASTM G 109 and C 1582.

WORKING PRINCIPLE

Nitrate in NitCal[™] reacts with iron to form hydroxide layers. Those layers prevent corrosion of steel reinforcements. The protective effect of NitCal[™] is comparable to that of nitrite, which has been used successfully for many years. NitCal[™] is the environmentally friendly alternative to nitrite.

TECHNICAL DATA

Homogeneity	homogenous	
Colour	colourless	
State	liquid	
Density	1.49 ± 0.03 g/cm ³	
pH-value	6 ± 1 (10% Solution)	
Workability	from +1 °C	
Shelf life	approx. 1 year from date of production if stored properly.	
Storage conditions	Store under cover, out of direct sunlight and protect from extremes of temperature.	



PROCESSING INDICATIONS

NitCal[™] is a ready to use admixture to be added to the ready-mixed concrete.

COMPATIBILITY

NitCal[™] is suitable for concrete designs containing OPC or SRC cement, micro-silica or silica fume, fly ash (PFA) and ground granulated blast furnace slag (GGBS).

When using other Ha-Be admixtures in the same concrete mixture, the products should be added separately and must not be blended prior to addition! Using more than one admixture requires suitability and preliminary tests in order to ensure the required combination of its effects is attained.

PACKAGING

- 30 I can
- 200 l barrel
- 1000 I container
- loose by bulk supply

HEALTH & SAFETY

This product is classified as hazardous according to the current regulations. Refer to the corresponding Material Safety Data Sheet for further advice.

REMARKS

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indications are neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use. This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

The management system of Ha-Be Egypt is certified to ISO 9001:2015.



Edition: 18 October 2021

SUITABILITY- AND PRELIMINARY TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!



NitCal™

Is matching all requirements according to ASTM (G 109 and C 1582):

CRITERIA	LIMIT REQUIREMENT	NITCAL™
Remaining compressive and flexural strength of concrete containing a chloride corrosion inhibiting admixture	min. 80% ^{A)}	②
Initial and final setting time	should not be altered more than 3.5 hours ^{A)}	(S)
The chloride-corrosion inhibitor complies with specification as admixture.	ASTM C494/C494M specification	⊘
Test of the admixture shall be done according to required method	ASTM G109	⊘
Integrated macro cell current	less than or equal to 50 C (Coulomb)	Ø
Corroded area	less or equal to 1/3 of the corroded area ^{A)}	②

A) Compared to reference