

DURAHIT® WP 500 (DM)

Item No 2290

Water resisting admixture acc. to DIN EN 934-2 for watertight concrete

FIELDS OF APPLICATION

DURAHIT® WP 500 (DM) is an efficient waterproofing agent especially designed for achieving depth hydrophobization by crystallisation for optimum water repellence in demanding concrete projects.

The water resisting admixture is suitable for concrete with advanced requirements in durability and quality and where optimum protection against water absorption is required.

DURAHIT® WP 500 (DM) is therefore particularly suitable for concrete applied in:

- Basements floors and walls
- Tunnel constructions
- Sewage treatment plants
- Water retaining constructions
- Drainage constructions
- Reinforced concrete constructions in marine environment

The waterproofing agent achieves a very effective protection mechanism which provides the following benefits:

- Optimum water repellence
- Decreased steel corrosion
- Enhanced resistance against visual deficiently signs like effloresces

DURAHIT® WP 500 (DM) advances concrete's durability and long-term performance and can make a contribution to ecological sustainability

DOSAGE

Recommended dosage range 0.5 – 2.0 mass-% of the cement content;
is equivalent to 5 – 20 ml per kg cement.

WORKING PRINCIPLE

DURAHIT® WP 500 (DM) reacts with calcium ions in concrete and forms a structure of water-insoluble crystals and generates a hydrophobic concrete texture thereby.

This hydrophobic effect reduces the capillary suction and decreases concrete's water absorption abilities.

TECHNICAL DATA

Homogeneity	homogenous
Colour	colourless
State	liquid
Density	1.02 ± 0.02 g/cm ³
Workability	from +5 °C
Chloride content	< 0.10 mass-%
Shelf life	approx. 1 year from date of production if stored properly
Storage conditions	Store in unopened, original sealed packaging between +5 °C and +25 °C. Protect from frost and insolation.

PROCESSING INDICATIONS

DURAHIT® WP 500 (DM) should be added either contemporaneously with the tempering water or to the ready-mixed concrete batch.

The mixing time must comply with the regulations defined in EN 206-1.

In order to ensure compatibility with other admixtures, pre-tests should be performed.

This product is classified as hazardous according to the CLP regulations. See safety data sheet for further information.

PACKAGING

- 30 l can
- 200 l barrel
- 1000 l container

REMARKS

This information describes the application- and processing possibilities of a product and its operation principles under regular conditions. Having no influence on the further application and processing, especially in conjunction with other construction materials, the given indication is neither a warranty in respect of the product's properties or its fitness for a particular purpose nor a full instruction of use. This information, any other recommendation or verbal advice are not binding and do not infer to any liability or legal demand.

Due to continuous further development, the most recent Technical Data Sheet is valid and will be supplied on request. All orders are accepted subject to our current general terms and conditions.

Edition: 31 March 2023

SUITABILITY- AND PRE-TESTS ARE NECESSARY BEFORE APPLYING THE CONCRETE ADMIXTURE!